

KOSYN LBR

KBR 701S

tcirubber



Typical Properties for KOSYN KBR:

cis-1,4 Content (%)	34.5
1,2-Vinyl Content (%)	14.5
Raw MV (ML ₁₊₄ , 100°C)	50
Volatile Matter (%)	0.5
Ash Content (%)	0.01
Toluene Insoluble Gel (%)	0.01
Gel Rank	A
Colour (APHA)	5
Cold Flow (mg/min)	1.0
Solution Viscosity (cps, 5% Styrene)	173

END USE:

Base polymer for use in HIPS (High Impact Polystyrene)

NOTE: The above data are typical value; therefore, they may differ slightly from the physical properties of the supplied product.

torchfire
tcirubber

Torchfire Canada Inc.

6597 Kitimat Road, Mississauga, Ontario L5N4J4

Tel 905 821-1183 | Toll-free 866 821-1183 | Fax 905 821-4188

www.tcirubber.com

