

# KOSYN NBR

## KNB 35H

tcirubber



### Typical Properties for KOSYN KNB:

Bound AN (%)	34
Raw MV (ML <sub>1+4</sub> , 100°C)	80
Specific Gravity	0.98
Compound Properties	
Compound MV (ML <sub>1+4</sub> , 100°C)	110
Rheometer (160° C, ARC ±1)	
ML (lbf - in)	16.5
MH (lbf - in)	46.3
Ts 1 (Min)	2.2
T' 50 (Min)	4.0
T' 90 (Min)	16.1
Cured*2	
300% Modulus (kgf/cm <sup>2</sup> )	168
Tensile Strength (kgf/cm <sup>2</sup> )	334
Elongation (%)	500
Hardness (Shore-A)	74
ATSM #1 Oil Immersion Change*3	
300% Modulus (%)	43
Tensile Strength (%)	-4
Elongation	-20
Hardness (Change %)	0
Volume (Change %)	0

NBR 100, ZnO 3, S/A 1, HAF Black (IRB#7) 40, Accelerator TBBS 0.7 Sulphur 1.75  
Total: 146.2

\*2) Press cured 40 Minutes at 150°C

\*3) 100°C X 70 Hours. Change Rate

NOTE: The above data are typical value; therefore, they may differ slightly from the physical properties of the supplied product.

torchfire  
tcirubber

### Torchfire Canada Inc.

6597 Kitimat Road, Mississauga, Ontario L5N4J4

Tel 905 821-1183 | Toll-free 866 821-1183 | Fax 905 821-4188

www.tcirubber.com

