

KOSYN S-SBR

SOL 5740

tcirubber



Typical Properties for KOSYN SOL:

Mooney Viscosity (ML ₁₊₄ , 100°C)	65
Vinyl Contents (wt% in butadiene Unit)	57
Bound Styrene (%)	15
Cured Rubber MV (ML ₁₊₄ , 100°C)	91.5
Rheometer (160° C, ARC ±1)	
ML (lbf - in)	8.7
MH (lbf - in)	42.9
Ts 1 (Min)	2.5
T' 50 (Min)	4.4
T' 90 (Min)	10.4
Cured* ²	
300% Modulus (kgf/cm ²)	230
Strength (kgf/cm ²)	177
Elongation (%)	360
Hardness (Shore-A)	67
Tear Resistance (B-Type, Kg/cm ²)	37
Rebound (ASTM.%)	56
Abrasion Loss * ³	0.1277
H.B.U. (°C) * ⁴	23.00

Polymer 100 ZnO 3, S/A 1, HAF Black (IRB#7) 50, DO 3, DM 0.6, Sulphur 1.75
Total: 156.65

*2) Press cured 35 Minutes at 145°C

*3) Akron type Tester

*4) Goodrich Flexometer

NOTE: The above data are typical value; therefore, they may differ slightly from the physical properties of the supplied product.

torchfire
tcirubber

Torchfire Canada Inc.

6597 Kitimat Road, Mississauga, Ontario L5N4J4

Tel 905 821-1183 | Toll-free 866 821-1183 | Fax 905 821-4188

www.tcirubber.com

