

KOSYN SBR LATEX

KSL 100 SERIES

tcirubber



Typical Properties for KOSYN KSL:

ITEM	KSL 103	KSL 106	KSL 107
Solid (wt %)	48.0	48.0	48.0
pH (25°C)	8.0	8.0	8.0
Surface Tension (dyne/cm ²)	50.0	50.0	55.0
Viscosity (cps)	200	140	200

END USE APPLICATIONS

Base Latex for Carpet Backing

Adhesive for fabrics

Binder for sand papers

Binder for non-woven fabrics & felts

NOTE:

The above data are typical value; therefore, they may differ slightly from the physical properties of the supplied product.

torchfire
tcirubber

Torchfire Canada Inc.

6597 Kitimat Road, Mississauga, Ontario L5N4J4

Tel 905 821-1183 | Toll-free 866 821-1183 | Fax 905 821-4188

www.tcirubber.com

