

KOSYN SBR LATEX

KSL 200 SERIES

tcirubber



Typical Properties for KOSYN KSL:

ITEM	KSL 202	KSL 203	KSL 208	KSL 210	KSL 220	KSL 230	KSL 232
Solid (wt %)	48.0	50.0	50.0	50.0	50.0	50.0	50.0
pH (25°C)	8.0	8.5	8.3	8.0	8.0	8.0	8.0
Surface Tension (dyne/cm ²)	54.0	50.0	52.0	54	55	57	56
Viscosity (cps)	85	70	210	200	250	250	300

END USE APPLICATIONS

Binder for paper coating
Art paper, LWC paper, Coated Paperboard
Cast Coated Paper
Specialty Papers

NOTE:

The above data are typical value; therefore, they may differ slightly from the physical properties of the supplied product.

torchfire
tcirubber

Torchfire Canada Inc.

6597 Kitimat Road, Mississauga, Ontario L5N4J4
Tel 905 821-1183 | Toll-free 866 821-1183 | Fax 905 821-4188
www.tcirubber.com

