

KOSYN SBR LATEX

KSL 300 SERIES

tcirubber



Typical Properties for KOSYN KSL:

ITEM	KSL 315	KSL 322	KSL 341	KSL 362	KSL 371
Solid (wt %)	50.0	40.0	69.0	48.5	52.0
pH (25°C)	10.5	10.5	10.5	10.0	10.5
Surface Tension (dyne/cm ²)	35.0	58.0	35.0	40	38
Viscosity (cps)	40	20	800	80	140

END USE APPLICATIONS

Road Paving Binder - Asphalt Modifier
Dip Solution for Tire Cord, Belt Fabrics and Hose Yarns
Foam rubber, Foam Backing, Resins for impact resistance, ABS Resins
Reinforcing for Cement, Water-proofing, Deck Covers

NOTE:

The above data are typical value; therefore, they may differ slightly from the physical properties of the supplied product.

torchfire
tcirubber

Torchfire Canada Inc.

6597 Kitimat Road, Mississauga, Ontario L5N4J4
Tel 905 821-1183 | Toll-free 866 821-1183 | Fax 905 821-4188
www.tcirubber.com

