

# KOSYN TPE

## SBS KTR 402

**tcirubber**



### Typical Properties for KOSYN KTR:

ITEM	TEST METHOD	
Structure		Radial
Physical Form		Porous Pellet*
Styrene Content (%)	IR	28
Volatile Matter (wt%)	ASTM D 1416	0.5
Solution Viscosity in 5.23% wt Toluene (cps)	ASTM D 445	18.0
Melt Flow Index 200°C, 5 kg (g/10min)	ASTM D 1238	< 1
Specific Gravity (g/cm <sup>3</sup> )	ISO 2781	0.94
Tensile Strength	ASTM D 412	120
300%Modulus (kgf/cm <sup>2</sup> )	ASTM D 412	29
Elongation @ Break	ASTM D 412	650
Hardness (Shore-A)	ASTM D 2240	81

\*Also available  
in Powder

### END USE APPLICATIONS: BITUMEN Modifier

#### NOTE:

The above data are typical value; therefore, they may differ slightly from the physical properties of the supplied product.

**torchfire**  
**tcirubber**

#### Torchfire Canada Inc.

6597 Kitimat Road, Mississauga, Ontario L5N4J4

Tel 905 821-1183 | Toll-free 866 821-1183 | Fax 905 821-4188

[www.tcirubber.com](http://www.tcirubber.com)

